



TRADITION SEIT 1919

UNI – Rollerstoff PIRMANN		Lichtwerte EN 410 / EN 14500 (380-780 nm)			Solarwerte EN 410 / EN 14500 (300-2500 nm)		
		Licht- Transmission	Licht- Reflexion	Licht- Absorption	Solar- Transmission	Solar- Reflexion	Solar- Absorption
13	weiß	26	72	2	26	62	12
06	gelb	15	76	9	18	66	16
07	grau	7	49	44	14	46	40
01	blau	1	12	87	2	26	72
05	elfenbein	20	78	2	22	67	11
10	hellgrün	8	58	34	15	58	27
08	grün	1	10	89	4	17	79
12	rot	1	14	85	7	30	63
09	hellblau	5	39	56	18	51	31
04	creme	18	68	14	17	55	28
02	beige	9	47	44	15	45	40
03	braun	1	14	85	2	16	82
11	hellorange	5	34	61	16	44	40
Blackout		0	83	17	0	70	30

Alle Angaben laut Hersteller!